

PROVIDES A VERY STABLE ROPE STRUCTURE AND ACHIEVES EXCELLENT BENDING FATIGUE RESULTS.


VEROTOP P

is a rotation-resistant rope with compacted strands and a rope core covered with a plastic layer.

- verotop P has a very high breaking strength.
- verotop P provides a very stable rope structure and achieves excellent bending fatigue results.
- verotop P offers excellent crushing and very good abrasion resistance.
- verotop P possesses perfect spooling behavior on multilayer drum.
- verotop P can be used either with or without swivel.
- verotop P is a category 1 rotation-resistant rope in accordance with ASTM A1023.

The rope is fully lubricated. The finish available as standard is galvanized, bright finish on request. Average fill factor: 0.730 Ordinary or Lang Lay available. Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309: RCN = 23-3 Further details: www.verope.com

VEROTOP P



Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
16	5/8	1.248	241.7	24.6	252.7	25.7
17		1.408	272.8	27.8	285.3	29.1
18		1.579	305.8	31.2	319.8	32.6
19	3/4	1.759	340.8	34.7	356.3	36.3
20		1.949	377.6	38.5	394.8	40.2
21		2.149	416.3	42.4	435.3	44.4
22		2.359	456.9	46.6	477.7	48.7
22.4		2.445	473.6	48.3	495.3	50.5
23		2.578	499.3	50.9	522.2	53.2
24		2.807	543.7	55.4	568.6	57.9
25		3.046	590.0	60.1	616.9	62.9
25.4	1	3.144	609.0	62.1	636.8	64.9
26		3.294	638.1	65	667.3	68
27		3.553	688.1	70.1	719.6	73.3
28		3.821	740.1	75.4	773.9	78.9
28.6	1-1/8	3.986	772.1	78.7	807.4	82.3
29		4.099	793.9	80.9	830.1	84.6
30		4.386	849.6	86.6	888.4	90.5
31		4.683	907.1	92.4	948.6	96.7
32	1-1/4	4.990	966.6	98.5	1011	103
33		5.307	1028	104.7	1075	109.5
34		5.634	1091	111.2	1141	116.3
35	1-3/8	5.970	1156	117.8	1209	123.2
36		6.316	1223	124.7	1279	130.4
38	1-1/2	7.037	1363	138.9	1425	145.2
40		7.797	1510	153.9	1579	160.9
42		8.597	1665	169.7	1741	177.4
43		9.011	1745	177.9	1825	186
44		9.435	1827	186.2	1911	194.7
45	1-3/4	9.869	1911	194.8	1999	203.7
46		10.312	1997	203.5	2089	212.8
48		11.228	2175	221.6	2274	231.7
50	2	12.183	2360	240.5	2468	251.5
52		13.178	2552	260.1	2669	272
54	2-1/8	14.211	2753	280.5	2878	293.3
56		15.86	2908	296.53	3058 ²	311.83 ²
58		17.01	3098	315.91	3258 ²	332.22 ²
60		18.20	3333	339.87	3505 ²	357.41 ²
62		19.44	3517	358.63	3698 ²	377.09 ²
64		20.71	3775	384.94	3969 ²	404.73 ²
66		21.37	3972	405.03	4094 ²	417.47 ²
68		23.38	4251	433.48	4470 ²	455.81 ²
70	2-3/4	24.78	4535	462.44	4769 ²	486.3 ²
72		26.21	4809	490.38	5057 ²	515.67 ²
74		27.69	5064	516.38		

Nominal rope diameter		Approx mass	Minimum breaking force tons ¹ of 2000 lbs		
			Rope grade		
			1960	2160	
mm*	Inch	lb/ft ¹	kg/ft ¹	1960	2160
16	5/8	0.84	0.38	27.2	28.4
17		0.95	0.43	30.7	32.1
18		1.06	0.48	34.4	35.9
19	3/4	1.18	0.54	38.3	40.1
20		1.31	0.59	42.4	44.4
21		1.44	0.66	46.8	48.9
22		1.58	0.72	51.4	53.7
22.4		1.64	0.75	53.2	55.7
23		1.73	0.79	56.1	58.7
24		1.89	0.86	61.1	63.9
25		2.05	0.93	66.3	69.3
25.4	1	2.11	0.96	68.5	71.6
26		2.21	1	71.7	75
27		2.39	1.08	77.3	80.9
28		2.57	1.16	83.2	87
28.6	1-1/8	2.68	1.22	86.8	90.8
29		2.75	1.25	89.2	93.3
30		2.95	1.34	95.5	99.9
31		3.15	1.43	102	106.6
32	1-1/4	3.35	1.52	108.6	113.6
33		3.57	1.62	115.5	120.8
34		3.79	1.72	122.7	128.3
35	1-3/8	4.01	1.82	130	135.9
36		4.24	1.93	137.5	143.8
38	1-1/2	4.73	2.15	153.2	160.2
40		5.24	2.38	169.8	177.5
42		5.78	2.62	187.2	195.7
43		6.06	2.75	196.2	205.1
44		6.34	2.88	205.4	214.8
45	1-3/4	6.63	3.01	214.9	224.7
46		6.93	3.14	224.5	234.8
48		7.55	3.42	244.5	255.6
50	2	8.19	3.71	265.2	277.4
52		8.85	4.02	286.9	300
54	2-1/8	9.55	4.33	309.4	323.5
56		10.66	4.83	326.9	343.7 ²
58		11.43	5.18	348.2	366.2 ²
60		12.23	5.55	374.6	394.0 ²
62		13.06	5.92	395.3	415.7 ²
64		13.92	6.31	424.3	446.1 ²
66		14.36	6.51	446.5	460.2 ²
68		15.71	7.13	477.8	502.4 ²
70	2-3/4	16.65	7.55	509.8	536.1 ²
72		17.61	7.99	540.6	568.4 ²
74		18.61	8.44	569.2	

verotop P/2024/10

© verope

*Standard tolerance: +2% to 4%, other tolerances possible upon agreement. Other and special rope diameters are available upon request.

1) The values are indicative only. Authoritative figures remain the metric ones! Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range. Subject to modifications, this may change the specifications.

Relevant is our website www.verope.com 2) *2060 N/mm²